

Property	Unit	Tolerance	Values								Standard
Scott Bond	J/m ²	Min 130	150	150	150	150	150	150	150	150	TAPPI T569
Scott Bond	ft.lbf/in ²		0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	TAPPI T569

Remarks

1. All properties are tested according to ISO and TAPPI Standard.
2. Tolerances, when specified, are based on 95% confidence limits on mill measurements of samples tested in standard conditions. According to ISO 187, (23°C/50% RH).

